


Granulats : **GRAVILLON 4/6 CONCASSE**
Péetrographie : Silico-Calcaire
Elaboration : Concassé

Classe granulaire		Partie contractuelle					Catégorie	
4	6.3	Norme NF P 18-545 Article 8 - EN 13043					Code III	
		d/2	d	D	1.4D	2D	Cg	FI
		0.063	2	4	6.3	9	12.5	
Etendue e			10	10				
V.S.S.+U		6	15	100				34.00
V.S.S.		5	10	98				30.00
V.S.I.			0	88	98	100		
V.S.I.-U			0	83	97			

Partie informative								
Résultats de production								
du 26/04/21 au 20/12/21								
	0.063	2	4	6.3	9	12.5	Cg	FI
Maximum	2.5	3	6	96	100	100	C90/1	6.80
Moyenne Xf	1.1	1	3	95	100	100	C90/1	6.06
Minimum	0.6	1	1	93	100	100	C95/1	4.30
Ecart-type	0.45	0.5	1.2	1.1	0.0	0.0	0.471	0.897
Nombre de résultats	15	15	15	15	15	15	3	5



DRUET Marion Responsable QSE

