


**Granulats :** **GRAVILLON 4/6 CONCASSE**  
**Pétrographie :** Silico-Calcaire  
**Elaboration :** Concassé

Classe granulaire		Partie contractuelle					Catégorie
4	6.3	Norme NF P 18-545 Article 8 - EN 13043					Code III
		d/2	d	D	1.4D	2D	
	<b>0.063</b>	<b>2</b>	<b>4</b>	<b>6.3</b>	<b>9</b>	<b>12.5</b>	<b>FI</b>
Etendue e			10	10			
V.S.S.+U		6	15	100			34.00
V.S.S.		5	10	98			30.00
V.S.I.			0	88	98	100	
V.S.I.-U			0	83	97		

Partie informative							
Résultats de production							
du 03/04/23 au 18/12/23							
	0.063	2	4	6.3	9	12.5	FI
Maximum	2.7	3	7	96	100	100	9.40
Moyenne Xf	1.5	2	4	94	100	100	6.98
Minimum	0.8	1	2	90	100	100	3.90
Ecart-type	0.58	0.8	1.5	1.8	0.0	0.0	2.409
Nombre de résultats	19	19	19	19	19	19	5



**DRUET Marion Responsable QSE**

