




**Granulats :** GRAVILLON 12,50/20 ROULE LAVE  
**Péetrographie :** Silico-Calcaire  
**Elaboration :** Roulé Lavé  
**Usage :** Bétons hydrauliques

Classe granulaire		Partie contractuelle						Catégorie	
12.5 / 20		Norme NF P 18-545 Article 10						Code A	
		d/2	d	D	1.4D	2D	FI	W	
		0.063	6.3	12.5	20	28	40		
Etendue e			15	15					
V.S.S.+U	1.8	6	20	100			24.00		
V.S.S.	1.5	5	15	99			20.00		
V.S.I.			0	84	98	100			
V.S.I.-U			0	79	97				

Partie informative								
Résultats de production								
du 09/01/23 au 26/06/23								
	0.063	6.3	12.5	20	28	40	FI	W
Maximum	0.5	1	15	96	100	100	12.00	2.1
Moyenne Xf	0.2	1	9	91	100	100	9.40	1.8
Minimum	0.0	0	5	87	100	100	6.80	1.5
Ecart-type	0.15	0.2	2.9	2.3	0.0	0.0	2.102	0.20
Nombre de résultats	25	25	25	25	25	25	6	25



**DRUET Marion Responsable QSE**