




**Granulats :** GRAVILLON 4/12,5 ROULE LAVE  
**Péetrographie :** Silico-Calcaire  
**Elaboration :** Roulé Lavé  
**Usage :** Bétons hydrauliques

Classe granulaire		Partie contractuelle							Catégorie
4	12.5	Norme NF P 18-545 Article 10							Code A
		d/2	d		D/1.4	D	1.4D	2D	
		0.063	2	4	8	9	12.5	18	25
Etendue e						30			
V.S.S.+U	2.5	6	16		74	100			
V.S.S.	1.5	5	15		70	99			
V.S.I.			0		40	90	98	100	
V.S.I.-U			0		36	88	97		

Partie informative								
Résultats de production								
du 15/04/24 au 03/12/24								
	0.063	2	4	8	9	12.5	18	25
Maximum	1.2	2	2	54	69	99	100	100
Moyenne Xf	0.6	1	1	46	59	96	100	100
Minimum	0.2	0	0	36	48	93	100	100
Ecart-type	0.34	0.4	0.5	7.0	7.9	1.8	0.0	0.0
Nombre de résultats	21	21	21	21	21	21	21	21



**DRUET Marion Responsable QSE**