


Granulats : GRAVE 0/10 SEMI-CONCASSEE
Péetrographie : Silico-Calcaire
Elaboration : Concassé
Usage : Routier

Partie contractuelle								
Classe granulaire			Norme			Catégorie		
0	10		Norme NF P 18-545 Article 7 - EN 13242			Code B		
	0.063	D/2	D	1.4D	2D	FM	MB	W
Etendue e	6	20	10					
V.S.S.+U	11.0	78	100	100			2.50	
V.S.S.	9.0	75	99	100			2.00	
V.S.I.	3.0	55	89	98	100			
V.S.I.-U	1.0	52	87	97	100			

Partie informative								
Résultats de production								
du 14/02/25 au 05/06/26								
	0.063	5	10	14	20	FM	MB	W
Maximum	7.1	61	98	100	100	4.02	0.74	5.5
Moyenne Xf	5.7	58	97	100	100	3.93	0.71	3.5
Minimum	4.8	55	96	100	100	3.81	0.49	2.1
Ecart-type	0.63	1.6	0.7	0.0	0.0	0.060	0.083	1.00
Nombre de résultats	18	18	18	18	18	18	16	18



DRUET Marion Responsable QSE