


38390 Porcieu-Amblagnieu

Granulats : Grave 0/80 Concassé

Résultats de production

	D/2			D			2D			du 14/10/21 au 05/01/23					
	0.063	0.08	1	2	4	8	12.5	20	40	63	80	100	125	150	VBS
Maximum	2.4	6	10	13	18	27	36	48	78	100	100	100	100	100	0.08
Moyenne Xf	2.0	4	7	9	12	21	30	40	67	89	95	100	100	100	0.08
Minimum	1.7	2	3	5	7	15	25	28	59	78	86	100	100	100	0.07
Ecart-type	0.30	1.5	2.6	3.3	4.2	4.4	3.8	5.8	6.6	6.5	4.7	0.0	0.0	0.0	0.000
Nombre de résultats	3	6	7	7	7	6	6	7	7	7	7	2	2	2	6



WIL 11.04.43.223 (c) Arcade

DRUET Marion Responsable QSE